

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

August 1, 2014

Mr. Samuel Jung
CONCERTEX, LLC
108 Fairway Court
Northvale, NJ 07647

Reference: Laboratory Test Report
Lab Identification No. 11132
Invoice No. 41985 (Attached)

Dear Mr. Jung:

One (1) fabric sample, identified as **ITEM: (SILICONE COATED FABRIC)**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

Test Results - Char

10mm 9mm 9mm


The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr
Attachment



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

August 1, 2014

Mr. Samuel Jung
CONCERTEX, LLC
108 Fairway Court
Northvale, NJ 07647

Reference: Laboratory Test Report
Lab Identification No. 11132
Invoice No. 41985 (Attached)

Dear Mr. Jung:

One (1) fabric sample, identified as **ITEM: (SILICONE COATED FABRIC)**, was received and tested in accordance with the UPHOLSTERED FURNITURE ACTION COUNCIL Fabric Classification Test Method--1990. The results are as follows:

Test Results
Vertical Char Lengths

8mm 9mm 9mm

Class


I

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr
Attachment



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

August 1, 2014

Mr. Samuel Jung
CONCERTEX, LLC
108 Fairway Court
Northvale, NJ 07647

Reference: Laboratory Test Report
Lab Identification No. 11132
Invoice No. 41985 (Attached)

Dear Mr. Jung:

One (1) fabric sample, identified as **ITEM: (SILICONE COATED FABRIC)**, was received and tested in accordance with the NFPA 260, "Cigarette Ignition Resistance of Components of Upholstered Furniture, 2009 Edition", (Cover Fabric Test). The results are as follows:

Test Results
Vertical Char Lengths

8mm 9mm 9mm


The sample submitted **meets** the requirements of the above standard and may be considered a **Class I Cover Fabric**. There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 45 mm.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr
Attachment



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

August 1, 2014

Mr. Samuel Jung
CONCERTEX, LLC
108 Fairway Court
Northvale, NJ 07647

Reference: Laboratory Test Report
Lab Identification No. 11132
Invoice No. 41985 (Attached)

Dear Mr. Jung:

One (1) fabric sample, identified as **ITEM: (SILICONE COATED FABRIC)**, was received and tested in accordance with the Motor Vehicle Safety Standard No. 302. The results are as follows:

TEST RESULTS

The sample submitted stopped burning before it had burned for 60 seconds from the start of timing, and had not burned more than two (2) inches from the point where timing was started.

The sample submitted **meets** the minimum requirements of the above standard. Fabric cannot burn at a rate of more than 4.00 inches/minute.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr
Attachment



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

August 1, 2014

Mr. Samuel Jung
CONCERTEX, LLC
108 Fairway Court
Northvale, NJ 07647

Reference: Laboratory Test Report
Lab Identification No. 11132
Invoice No. 41985 (Attached)

Dear Mr. Jung:

One (1) fabric sample, identified as **ITEM: (SILICONE COATED FABRIC)**, was received and tested in accordance with **INTERNATIONAL MARITIME ORGANIZATION, Resolution A.652(16) Methods of Test for the Ignitability by Smokers' Materials of Upholstered Composites for Seating.** Per Appendix A, A.1(b), "The tests only measure the ignitability of a combination of materials used in upholstered seating and not of a particular finished item of furniture incorporating these materials. They give an indication of, but cannot guarantee, the ignition behaviour of the finished item of furniture".

The fabric sample submitted was tested to Section 8.2 Smouldering Cigarette Test. The results are as follows:

<u>Ignition Source</u>		<u>Test Results</u>
Smoldering Cigarette	#1	PASS (No flaming or progressive smouldering)
	#2	PASS (No flaming or progressive smouldering)

The sample submitted, **meets** minimum requirements of the above standard when tested to smouldering cigarette ignition.

If there are any questions or when we can be of further assistance, please let us know.


Sincerely,

Bobby E. Puett

BEP/mr

Attachment

OUR LETTERS AND REPORTS ARE FOR THE EXCLUSIVE USE OF THE CLIENT TO WHOM THEY ARE ADDRESSED. ANY COMMUNICATION TO OTHERS OR THE USE OF OUR COMPANY NAME MUST RECEIVE PRIOR APPROVAL. OUR TEST RESULTS APPLY ONLY TO THE SAMPLE TESTED AND ARE NOT NECESSARILY INDICATIVE OF THE QUALITIES OF APPARENTLY IDENTICAL OR SIMILAR PRODUCTS. SAMPLES NOT DESTROYED IN TESTING ARE RETAINED A MAXIMUM OF THIRTY DAYS. THE LETTERS, REPORTS OR NAME OF DIVERSIFIED TESTING LABORATORIES, INC. MAY NOT BE USED IN ADVERTISING TO THE GENERAL PUBLIC.



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

August 1, 2014

Mr. Samuel Jung
CONCERTEX, LLC
108 Fairway Court
Northvale, NJ 07647

Reference: Laboratory Test Report
Lab Identification No. 11132
Invoice No. 41985 (Attached)

Dear Mr. Jung:

One (1) fabric sample, identified as **ITEM: (SILICONE COATED FABRIC)**, was received and tested in accordance with **INTERNATIONAL MARITIME ORGANIZATION, Resolution A.652(16) Methods of Test for the Ignitability by Smokers' Materials of Upholstered Composites for Seating.** Per Appendix A, A.1(b), "The tests only measure the ignitability of a combination of materials used in upholstered seating and not of a particular finished item of furniture incorporating these materials. They give an indication of, but cannot guarantee, the ignition behaviour of the finished item of furniture".

The fabric sample submitted was tested to Section 8.3 Butane Flame Test. The results are as follows:

<u>Ignition Source</u>	<u>Test Results</u>
Butane Flame	#1 PASS (No flaming or progressive smouldering)
	#2 PASS (No flaming or progressive smouldering)

The sample submitted **meets** minimum requirements of the above standard when tested to the butane flame ignition source.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr

Attachment

ALL TESTS AND REPORTS ARE FOR THE EXCLUSIVE USE OF THE CLIENT TO WHOM THEY ARE ADDRESSED. ANY COMMUNICATION TO OTHERS OR THE USE OF OUR COMPANY NAME MUST RECEIVE PRIOR APPROVAL. OUR TEST RESULTS APPLY ONLY TO THE SAMPLE TESTED AND ARE NOT NECESSARILY INDICATIVE OF THE QUALITIES OF APPARENTLY IDENTICAL OR SIMILAR PRODUCTS. SAMPLES NOT DESTROYED IN TESTING ARE RETAINED A MAXIMUM OF THIRTY DAYS. THE LETTERS, REPORTS OR NAME OF DIVERSIFIED TESTING LABORATORIES, INC. MAY NOT BE USED IN ADVERTISING TO THE GENERAL PUBLIC.