

MESSRS:
ZOLI DINO & C SRL
VIALE BOLOGNA,286/A
47122 FORLI (FC)
ITALIA

REPORT NR. 1704349-002
REPORT DATE 27/12/2017
ACCEPTANCE DATE 21/12/2017
START TEST DATE 21/12/2017
END TEST DATE 27/12/2017
SAMPLING BY CUSTOMER

TEST REPORT


SAMPLE DESCRIPTION BOB

THE REPORT IS MADE BY THE FOLLOWING TESTS:

| TEST | METHOD | ACCREDIA |
|---|-------------|----------|
| 6011001 Ignitability of upholstery fabric - California test | TB 117:2013 | |

Technical Manager

Dott.ssa Valentina Guidotti



Managing Director

Patrizia Rosati



(*) = Test marked with asterisk are not accredited ACCREDIA.

Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it can't also be used to imply the products certification.

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 - 59013 Oste - Montemurlo (PO)
Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it

TEST REPORT

MESSRS:
ZOLI DINO & C SRL
VIALE BOLOGNA,286/A
47122 FORLI (FC)
ITALIA

| | |
|-----------------------------|--------------------|
| REPORT NR. | 1704349-002 |
| REPORT DATE | 27/12/2017 |
| ACCEPTANCE DATE | 21/12/2017 |
| START TEST DATE | 21/12/2017 |
| END TEST DATE | 27/12/2017 |
| SAMPLING BY CUSTOMER | |

NOTES ANALYTICAL TESTS

- **6011001 Ignitability of upholstery fabric - California test** **TB 117:2013**
Acclimatization: At least 24 hours at 21 ± 3 °C e <55 R.H. %.
Codes used:
SE: Self-extinguished;
SB45: Smolder beyond 45 min;
TOF: Transitions to open flaming;
MNR: Measurement not recorded as smoldering exceeded 45 min or specimen transitioned to open flames.
The data are referred to TB 117:2013 - Section NR.1
Filling material: PU-nonFR (28-29,6 Kg/m³) supplied by the laboratory.

GENERAL NOTES

(*) = Test marked with asterisk are not accredited ACCREDIA.

Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it can't also be used to imply the products certification.

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)
Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it

TEST REPORT

MESSRS:
ZOLI DINO & C SRL
VIALE BOLOGNA,286/A
47122 FORLI (FC)
ITALIA

REPORT NR. 1704349-002
REPORT DATE 27/12/2017
ACCEPTANCE DATE 21/12/2017
START TEST DATE 21/12/2017
END TEST DATE 27/12/2017
SAMPLING BY CUSTOMER

| Tests | M.U. | Results | Method |
|--|-------|-------------|--------------------|
| 6011001 Ignitability of upholstery fabric - California test | | | T8 117:2013 |
| Initial - Specimen 1 - Char length | inch | 0 | |
| Initial - Specimen 2 - Char length | inch | 0 | |
| Initial - Specimen 3 - Char length | inch | 0,1 | |
| Initial - Specimen 1 - SE | Si/No | YES | |
| Initial - Specimen 2 - SE | Si/No | YES | |
| Initial - Specimen 3 - SE | Si/No | YES | |
| Initial - Specimen 1 - SB45 | Si/No | NO | |
| Initial - Specimen 2 - SB45 | Si/No | NO | |
| Initial - Specimen 3 - SB45 | Si/No | NO | |
| Initial - Specimen 1 - TOF | Si/No | NO | |
| Initial - Specimen 2 - TOF | Si/No | NO | |
| Initial - Specimen 3 - TOF | Si/No | NO | |
| Replacement - Specimen 1 - Char length | inch | 0,1 | |
| Replacement - Specimen 2 - Char length | inch | 0,1 | |
| Replacement - Specimen 3 - Char length | inch | 0 | |
| Replacement - Specimen 1 - SE | Si/No | YES | |
| Replacement - Specimen 2 - SE | Si/No | YES | |
| Replacement - Specimen 1 - SE | Si/No | YES | |
| Replacement - Specimen 1 - SB45 | Si/No | NO | |
| Replacement - Specimen 2 - SB45 | Si/No | NO | |
| Replacement - Specimen 2 - SB45 | Si/No | NO | |
| Replacement - Specimen 1 - TOF | Si/No | NO | |
| Replacement - Specimen 2 - TOF | Si/No | NO | |
| Replacement - Specimen 3 - TOF | Si/No | NO | |
| Final class | | PASS | |

----- **END OF REPORT** -----

(*) = Test marked with asterisk are not accredited ACCREDIA.

Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it can't also be used to imply the products certification.

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)
 Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it