

MESSRS:
ZOLI DINO & C SRL
VIALE BOLOGNA,286/A
47122 FORLI (FC)
ITALIA

REPORT NR. 1801453-005
REPORT DATE 20/04/2018
ACCEPTANCE DATE 17/04/2018
START TEST DATE 17/04/2018
END TEST DATE 20/04/2018
SAMPLING BY CUSTOMER

TEST REPORT


SAMPLE DESCRIPTION PACIFICO

THE REPORT IS MADE BY THE FOLLOWING TESTS:

TEST	METHOD	ACCREDIA
6011001 Ignitability of upholstery fabric - California test	TB 117:2013	

Technical Manager

Dott.ssa Valentina Guidotti



Managing Director

Pat Rosatizia



(*) = Test marked with asterisk are not accredited ACCREDIA.

Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it cant't also be used to imply the products certification.

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)
Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it

TEST REPORT

MESSRS:
ZOLI DINO & C SRL
VIALE BOLOGNA,286/A
47122 FORLI (FC)
ITALIA

REPORT NR.	1801453-005
REPORT DATE	20/04/2018
ACCEPTANCE DATE	17/04/2018
START TEST DATE	17/04/2018
END TEST DATE	20/04/2018
SAMPLING BY CUSTOMER	

NOTES ANALYTICAL TESTS

- **6011001 Ignitability of upholstery fabric - California test** **TB 117:2013**
Acclimatization: At least 24 hours at 21 ± 3 °C e <55 R.H. %.
Codes used:
SE: Self-extinguished;
SB45: Smolder beyond 45 min;
TOF: Transitions to open flaming;
MNR: Measurement not recorded as smoldering exceeded 45 min or specimen transitioned to open flames.
The data are referred to TB 117:2013 - Section NR.1
Filling material: PU-nonFR (28-29,6 Kg/m³) supplied by the laboratory.

GENERAL NOTES

(*) = Test marked with asterisk are not accredited ACCREDIA.

Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it can't also be used to imply the products certification.

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)
Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it

TEST REPORT

MESSRS:
ZOLI DINO & C SRL
VIALE BOLOGNA,286/A
47122 FORLI (FC)
ITALIA

REPORT NR. 1801453-005
REPORT DATE 20/04/2018
ACCEPTANCE DATE 17/04/2018
START TEST DATE 17/04/2018
END TEST DATE 20/04/2018
SAMPLING BY CUSTOMER

Tests	M.U.	Results	Method
6011001 Ignitability of upholstery fabric - California test			TB 117:2013
Initial - Specimen 1 - Char length	inch	0,5	
Initial - Specimen 2 - Char length	inch	0,5	
Initial - Specimen 3 - Char length	inch	0,4	
Initial - Specimen 1 - SE	Yes/No	NO	
Initial - Specimen 2 - SE	Yes/No	NO	
Initial - Specimen 3 - SE	Yes/No	NO	
Initial - Specimen 1 - SB45	Yes/No	NO	
Initial - Specimen 2 - SB45	Yes/No	NO	
Initial - Specimen 3 - SB45	Yes/No	NO	
Initial - Specimen 1 - TOF	Yes/No	NO	
Initial - Specimen 2 - TOF	Yes/No	NO	
Initial - Specimen 3 - TOF	Yes/No	NO	
Final class		PASS	

----- **END OF REPORT** -----

(*) = Test marked with asterisk are not accredited ACCREDIA.

Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it can't also be used to imply the products certification.

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)
 Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it